

Applicant: WENZHOU SOGU TECHNOLOGY CO.,LTD
NO.33 BEIWEI 1ST ROAD,WENZHOU ,CHINA

Date: Jul 13, 2023

Attn: LIU YANMU

Sample Description:

Three (3) pieces of submitted samples said to be Strobel Antistatic PP Insoles 2.0mm Grey Code: IPDT.

Standard : EN ISO 20345: 2011
SATRA TM240: 2001

Colour : Grey

Manufacturer : E-MART

Supplier : E-MART

Country Of Origin : CHINA


Date Received/Date Test Started : Jul. 04, 2023

Date Final Information Confirmed: --

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Huang Ning, Andy
Assistant General Manager



- 1 Electrical Resistance Of Footwear Components (SATRA TM240: 2001, Dry: 20°C, 30% R.H. For 7 Days, Wet: 20°C, 85% R.H. For 7 Days)

| Condition | Specimen | Results | Requirement | Pass/Fail |
|-----------|------------|----------|-------------|-----------|
| Dry | Specimen 1 | 2.35 MΩ | | Pass |
| | Specimen 2 | - | | - |
| | Specimen 3 | - | | - |
| | Specimen 4 | - | | - |
| | Specimen 5 | - | | - |
| | Specimen 6 | - | | - |
| Wet | Specimen 1 | < 0.1 MΩ | | Pass |
| | Specimen 2 | - | | - |
| | Specimen 3 | - | | - |
| | Specimen 4 | - | | - |
| | Specimen 5 | - | | - |
| | Specimen 6 | - | | - |

- 2 Thickness (Insole) (EN ISO 20344:2011(7.1))

| Sample | Results | Requirement | Pass/Fail |
|--------|---------|-------------|-----------|
| - | 2.1 mm | Min. 2.0 mm | Pass |

Expanded Uncertainty: 0.07 mm, With k= 1.96 At 95% Confidence Level.

- 3 Water Absorption & Desorption (Insole) (EN ISO 20344:2011(7.2))

| Sample | Results | | Requirement | Pass/Fail |
|--------|------------------------|------------------|-------------|-----------|
| | Water Absorption | Water Desorption | | |
| - | 165 mg/cm ² | 101% | * | Pass |

Remark: * = Water Absorption: Min. 70 mg/cm²
Water Desorption: Min. 80%

Expanded Uncertainty:

Water Absorption: 0.10 mg/cm², With k= 1.96 At 95% Confidence Level.

Water Desorption: 0.03%, With k= 1.96 At 95% Confidence Level.

4 Abrasion Resistance (Insole) (EN ISO 20344:2011(7.3))

| Sample | Result | Requirement | Pass/Fail |
|--------|---|-------------|-----------|
| 二 | No More Than Severe Damage Before 400 Cycles. | * | Pass |

Remark: * = There Shall Be No More Than Severe Damage Before 400 Cycles.

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

GZHT90810660

